

## Ground Low Calcined Alumina

# AR4TA

### PRODUCT INFORMATION

Reactive aluminium oxide (Al<sub>2</sub>O<sub>3</sub>), with a medium soda content.

### CHARACTERISTICS

Physical Characteristics	Unit	Typical Value
<u>Particle Size Distribution (Malvern)</u>		
D50	µm	90
< 45µm	%	8
< 150µm	%	97
Screen residue >200µm	%	0.00
BET Surface Area	m <sup>2</sup> /g	5
Acid Oleic absorption	ml/100g	50
Cut	-	6
Polish	-	3
Chemical Characteristics	Unit	Typical Value
Na <sub>2</sub> O total	ppm	2500
CaO	ppm	150
SiO <sub>2</sub>	ppm	150
Fe <sub>2</sub> O <sub>3</sub>	ppm	150

Valid after: 01/2013

C.A.S.: 1344-28-1