GK-455

Technical spezification

Chemical data



	Typical data
Al_2O_3	40 - 45%
Fe_2O_3	< 0,5 %
Na ₂ O	< 0,5 %
CaO	< 0,4 %
TiO ₂	< 0,3 %

	Typical data		
SiO ₂	47- 52 %		
Cr_2O_3	< 0,1 %		
K ₂ O	< 5 %		
Mn_2O_3	< 1 %		
MgO	< 1 %		

Polishing

Physical data

Typical data

2 - 6 µm		
32 - 42 μm		
82 - 92 μm		
About 3 %		
18 - 26 Gew	. %	housemethod
1090 - 1200	g/l	*DIN ISO 787 T11
7		
2		
EG	Best befor	e Unlimited with proper storage
	32 - 42 μm 82 - 92 μm About 3 % 18 - 26 Gew 1090 - 1200 7 2	32 - 42 μm 82 - 92 μm About 3 % 18 - 26 Gew. % 1090 - 1200 g/l 7 2

* In accordance to

Llast check on 01.03.23 by CFK Our technical advice on applications and the preparation of data sheets verbally, in writing and by means of tests are given to the best of our knowledge, but are regarded only as non-binding information, also with regard to any property rights of third parties, and do not release you from your own examination of the products supplied by us for their suitability for the intended processes and purposes. Application, use and processing of the products are beyond our control and are therefore exclusively your responsibility. The technical data are subject to constant quality control and will be adjusted if necessary in the course of production optimisation.

Mipri GmbH Königsberger Straße 26 55543 Bad Kreuznach GERMANY USt-Id-Nr: DE 225684785
 Internet:
 www.mipri.com

 Phone:
 +49 671 794 653 30

 Fax:
 +49 671 794 653 31

 E-Mail:
 office@mipri.com

 IBAN
 DE55664400840459090700

